

Product Description	EGO SB 25 is a softplastic putty.	
Typical Applications	For single glazing in timber and metal windows and their combinations according to stress groups 1 to 5 of DIN 18545-3: Glazing Systems and to RoTa chart (determination of stress groups for glazing windows) worked out by the Institut für Fenstertechnik e. V., Rosenheim.	
Application	Apply EGO SB 25 only onto dry and clean profiles that are free from substances liable to impair adhesion. Timber frames (moisture max. 15 %) must be painted prior to the application. Apply EGO SB 25 in sufficient quantity and without bubbles.	
Please observe	DIN 18361 (Glazing work) DIN 18545 (Sealing of glazing with sealants) DIN 18363 (Paintwork) Technical directives for window paints Instructions 3 + 18 by Bundesausschuß Farbe und Sachwertschutz as well as EGO glazing systems In case of profiles made of galvanised steel, non-ferrous metal and marble please contact us.	
Density	Approx. 2 g/cm ³	DIN EN ISO 10563
Application Temperature	+ 5° c to + 30° C	
Service Temperature	Approx, - 30° C to + 80° C	
Consistency	Softplastic	
Properties	Non-shrinking , thixotropic	
Meets the Requirements of	DIN 18545-B	
Method of Application	Manually or with EGOFIX Compressed Air Gun	
Secondary Treatment	Smooth carefully with a polished putty knife Over-paint all putty surface with a weatherproof paint at the earliest after skin formation, at the latest after 8 weeks.	
Standard Colours	Brown, grey	
Packaging	10 kg bucket 25 kg bucket 50 mm Ø sausages, 10 kg/box 70 mm Ø sausages, 25 kg/box	
	Special packaging upon request.	
Storage	Store in cool and dry conditions in closed original packaging. Shelf life 12 months	